



Xcellite™ 2996.4 Typical Data Sheet

Engineered Foam Description	Super ultra soft, semi-closed cellular rubber
Polymer	EPDM
Standard Color	Black (Please call for optional colors)
ASTM D1056 Classification	1A0 Z1=2 kPa max at 50% compression Deflection (optional suffixes can be added)

Physical Property	Target	Units	Test Method
Density	64 - 128	kg/m ³	ASTM D1056
	4 - 8	lbs/ft ³	
Compression Deflection, 25%	2 max.	kPa	ASTM D1056
	0.3 max.	psi	
Compression Deflection, 50%	2 max.	kPa	ASTM D1056
	0.3 max.	psi	
Compression Set, 50% RT	10	%	ASTM D1056
Tensile	220	kPa	ASTM D1056
	30	psi	
Elongation	200	%	ASTM D1056
Water Absorption* <small>* tested per 42.1 added skin clause</small>	10 max.	%	ASTM D1056
Flammability, burn rate	100 max.	mm/min.	FMVSS 302
	4 max.	in./min.	
Temperature Use: Hot ¹	148 / 300	°C / °F	ASTM D1056
: Cold	-54 / -65	°C / °F	
Gauge ^{2, 3} skin two sides	6 - 30	mm	ASTM D1056
	0.236 - 1.181	in.	

NOTE:

- 1 - For intermittent exposure only
- 2 - Please contact customer service 574.284.1000 for additional sizes including widths, skin one side and no skin surfaces.**
- 3 - RMA Class 3 surfaces

SAE J18 1A0

For details or information on additional standards please contact customer service.

The technical service information presented on this Typical Data Sheet has been derived from data using standardized test methods/practices. Fostek Corp. does not control the end use/modification of its products and therefore does not represent or warrant its products to be suitable for any specific end use. Fostek recommends that its material be tested for fitness of use and safety in the manner in which it may be utilized.