

Developer & Manufacturer of Engineered Foams

## Xcellite<sub>™</sub> 3996.3 Gray Typical Data Sheet

Engineered Foam Description	
Polymer	
Color	

Ultra soft, semi-closed cellular rubber EPDM Medium Gray\*

ASTM D1056 Classification

1A0 Z1=2 kPa max (optional suffixes can be added)

Physical Property	Target	Units	Test Method	
Density	56 - 112	kg/m <sup>3</sup>	ASTM D1056	
	3.5 - 7.0	lbs/ft <sup>3</sup>		
Compression Deflection,25%	2 max.	kPa	ASTM D1056-07	
	0.3 max.	psi		
Compression Set, 50% RT	10	%	ASTM D1056	
Tensile	150	kPa	ASTM D1056	
	22	psi		
Elongation	200	%	ASTM D1056	
ater Absorption*	10 max.	%	ASTM D1056	
* tested per 43.1 added skin clause	TO IIIdX.		70	ASTIM D1050
Flammability, burn rate	100 max.	mm/min.	FMVSS 302	
	4 max.	in./min.	1101033 302	
Temperature Use: Hot <sup>1</sup>	148 / 300	°C / °F		
: Cold	-54 / -65	°C / °F	ASTM D1056	
Gauge <sup>2, 3</sup> skin two sides	3 and above	mm	ASTM D1056	
	0.118 and above	in.		

NOTE:

\* Color Medium Gray may have black marks/streaks within the color of the foam

For reference:

1 - For intermittent exposure only

2 - Please contact customer service 574.284.1000 for additional sizes including widths, skin one side and no skin surfaces.

3 - RMA Class 3 surfaces

The technical service information presented on this Typical Data Sheet has been derived from data using standardized test methods/practices. Fostek Corp. does not control the end use/modification of its products and therefore does not represent or warrant its products to be suitable for any specific end use or that the results shown on this Typical Data Sheet will be achieved by a user for a particular purpose. Fostek recommends that its material be tested for fitness of use and safety in the manner in which it may be utilized.